

RS-440-XSR 8-MIL

MADICO PROTEKT™ FILM

Benefits:


- Superior heat rejection
- Reduced fading of interior furnishings by screening out harmful UV rays
- Improved comfort by blocking sun’s heat and glare
- Energy savings through lower air conditioning costs
- Scratch -resistant

Performance Data:

Total Solar Energy:	
Transmitted	24%
Reflected	36%
Absorbed	40%
Visible Light:	
Transmitted	36%
Reflected	42%
“U” Factor:	
Median	.94
Design	.99
Ultra Violet Light Rejected	99%
Shading Coefficient	.39
Total Solar Energy Rejected	66%

Physical Properties:

Film Thickness	.008”
Structure	Multi-Ply Laminate
Tensile Strength	32,000 PSI Average MD/TD
Break Strength	240 Pounds Per Inch (Width)
Adhesive Type	Acrylic Pressure Sensitive
Peel Strength	5 to 6 Pounds Per Inch



ISO 9001: 2000 Certified

45 Industrial Parkway, Woburn, MA 0180 • 800-225-1926 • www.madico.com

Since only the user is aware of the specific condition in which the product is to be used, it is the user’s responsibility to determine whether the product is suitable for that intended use. If the specific conditions of use are critically dependent on any of the properties of the product, or if you need further information of any sort, contact Madico or your local Madico window film dealer.



V-9422-RO5