

SDSS-220-XK

Solar Optical Performance Data

Center of Glass Measurements:*

Total Solar Energy:

Transmitted 13%
 Reflected 62%
 Absorbed 25%

Visible Light:

Transmitted 18%
 Reflected Interior..... 60%
 Reflected Exterior..... 57%

U Value1.04
 Emissivity.....0.85
 Ultraviolet Light Rejected 99%

Glare Reduction.....80%
 Shading Coefficient 0.23
 Solar Heat Gain Coefficient.....0.20

Total Solar Energy Rejected80%



Window Performance:**

SDSS-220-XK					
Type	Default Glazing Reference	SHGC No Film	SHGC With Film	VLT No Film	VLT With Film
Residential	3 mm (1/8in.) clear	0.71	0.20	0.74	0.14
Residential†	3 mm (1/8in.) clear 3 mm (1/8in.) clear	0.63	0.27	0.67	0.14
Non Residential	6 mm (1/4in.) clear	0.75	0.23	0.80	0.15
Non Residential	6 mm (1/4in.) grey	0.53	0.28	0.40	0.08
Non Residential†	6 mm (1/4in.) clear 6 mm (1/4in.) clear	0.65	0.31	0.71	0.14
Non Residential†	6 mm (1/4in.) grey 6 mm (1/4in.) clear	0.42	0.26	0.36	0.07

* Read in accordance with National Fenestration Rating Council (NFRC) standards on 3mm. clear glass.

**As certified by the National Fenestration Rating Council (NFRC).

† Dual pane window



ISO 9001: 2000 Certified

64 Industrial Parkway, Woburn, MA 01801 • 800-225-1926 • www.madico.com

